

Product Description

CAPILENE® CT 71 A is a specialty polypropylene combining typical advantages of polypropylene random and heterophasic copolymers.

- | | | |
|----------------------------|---|---|
| Features: | <ul style="list-style-type: none"> • Excellent impact • Very low stress whitening • Mold release • Good organoleptic properties | <ul style="list-style-type: none"> • Good transparency • High gloss • Clarified • Short cycle time |
| Uses: | <ul style="list-style-type: none"> • Thin wall packaging • Large storage boxes • Clear pails • Clear containers | <ul style="list-style-type: none"> • Household articles • Heavy duty toolboxes • Caps and closures • Toys |
| Processing Methods: | <ul style="list-style-type: none"> • Injection molding | |

Properties		Method	Typical Value*	Unit
Physical				
Melt Flow Rate	(230°C/2.16 kg)	ISO 1133	25	g/10 min
Mechanical				
Tensile Stress at Yield	(50 mm/min)	ISO 527-2	24	MPa
Tensile Strain at Yield	(50 mm/min)	ISO 527-2	17	%
Flexural Modulus	(5 mm/min)	ISO 178	900	MPa
Izod Impact Strength, notched	(+23°C)	ISO 180	18	kJ/m ²
Izod Impact Strength, notched	(-20°C)	ISO 180	3	kJ/m ²
Thermal				
Vicat Softening Temperature	(10 N)	ISO 306	135	°C
Heat Deflection Temperature	(0.45 MPa)	ISO 75-2	79	°C
Optical				
Haze	(1 mm plaque)	ASTM D1003	30	%

*Typical values; not to be construed as specifications.

Health, Quality, Regulations and Safety

This product is not classified as dangerous substance. Material safety data sheets, international standards certificates (e.g. ISO 9001) and other regulatory documents are available on our website. This product is not intended for use in medical or pharmaceutical applications and we do not support its use for such applications.