



Luban DGDZ-2400

High Density Polyethylene



Description

Luban DGDZ-2400 is high molecular weight high-density polyethylene with broad molecular weight distribution. The grade is intended for use in PE-80 pressure pipe applications where long-term hydrostatic strength and resistance to slow crack growth are desired. The grade has good processability, exceptional melt strength and ideally suited for both large and small diameter pipes. Carbon black (CB) should be added to the granular PE via LLDPE based masterbatch to obtain ca 2.25% CB in the pipe resin. The carbon black should have a particle size 10-25nm and be well dispersed in the final black pipe grade.

Main Characteristics:

- Hexene High Density Resin
- Exceptional Melt Strength
- PE-80 Pressure Pipe Grade

Application

PE-80 pipes for water, sewerage and gas distribution, corrugated pipes

Properties (Typical Values)

Property	Unit	Test method	Value
Melt Index (190°C/5 kg)	g/10 min	ASTM D1238	0.38
Melt Index (190°C/21.6 kg)	g/10 min	ASTM D1238	10
Density	g /cm ³	ASTM D1505	0.940
Flexural modulus (2% Secant)	MPa	ASTM D790B ¹	690
Tensile stress at yield	MPa	ASTM D638 ¹	18
Tensile stress at break	MPa	ASTM D638 ¹	30
Tensile strain at break	%	ASTM D638 ¹	600
PENT (slow crack growth; 80°C, 2.4 MPa)	hr	ASTM F1473	>3000
Designation		ISO 12162	PE-80
Minimum Required Strength (MRS)	MPa	ISO 9080	>8
Slow Crack Growth Resistance ² - Notched Pipe	hr	ISO 13479	>500

¹Molded and tested in accordance with ASTM D4976.

²Tested on 110mm SDR11 pipe.

Note: These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.





Luban DGDZ-2400 High Density Polyethylene



Storage and Handling

Luban DGDZ-2400 should be stored in well ventilate area during handling or processing of to prevent accumulation of dust and fumes. Avoid contact with strong oxidizers, excessive heat, sparks or open flame as this could well speed up alteration and consequently loss of quality of the material in which could lead to unforeseen dangers. The bags must be protected from direct sunlight and should be stored in shaded and completely dry area for good processing.

Safety

Luban DGDZ-2400 is not classified as dangerous preparation. For further information about safety in handling and processing please refer to the Safety Data Sheet.

Food Contact

Luban DGDZ-2400 meets the requirements of the U.S. Food and Drug Administration (FDA) as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Product Stewardship Declaration".

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Updated: Oct. 2019

Disclaimer:

Values given here are typical and should not be interpreted as specification. Before using ORPIC product, customers and other users should make their own independent determination that the product is suitable for the intended use. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under ORPIC or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of ORPIC except in a writing signed by an authorized ORPIC employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at ORPIC's option, and in no event shall ORPIC be liable for special, consequential, incidental, punitive or exemplary damages.

