



Luban DMDA-8007

High Density Polyethylene



Description

Luban DMDA-8007 is a narrow molecular weight distribution high density homopolymer designed to offer excellent stiffness, low warpage, good/ acceptable toughness, and good moldability. This grade is ideally suited for injection molded products requiring high rigidity. This resin is also suitable for cast film extrusion processing.

Main Characteristics:

- Excellent stiffness/modulus
- Excellent warp resistance
- Molded parts have high gloss, low odor
- For injection molded crates, cases, totes, and other parts needing high modulus
- For cast film extrusion

Application

Injection molded crates, cases, trays, tote bins, injection molded caps and closures for beverages

Properties (Typical Values)

| Property | Unit | Test method | Value |
|--|--------------------|-------------------------|-------|
| Melt Index (190°C/2.16 kg) | g/10 min | ASTM D1238 | 8 |
| Melt Index (190°C/21.6 kg) | g/10 min | ASTM D1238 | 180 |
| Density | g /cm ³ | ASTM D792 | 0.965 |
| Environmental Stress-Cracking Resistance 122°F (50°C), 100% Igepal, F50 | hr | ASTM D1693 ¹ | 2 |
| Flexural Modulus - 2% Secant | MPa | ASTM D790B ¹ | 1410 |
| Tensile stress at yield | MPa | ASTM D638 ¹ | 31 |
| Tensile strain at yield | % | ASTM D638 ¹ | 6 |
| Tensile stress at break | MPa | ASTM D638 ¹ | 17.9 |
| Tensile strain at break | % | ASTM D638 ¹ | 350 |
| Tensile Impact Strength | kJ/m ² | ASTM D1822 ¹ | 168 |
| Durometer Hardness (Shore D) | | ASTM D2240 ¹ | 61 |
| Deflection Temperature Under Load 0.45 MPa, Unannealed | °C | ASTM D648 ¹ | 84 |
| Vicat Softening Temperature | °C | ASTM D1525 | 131 |

¹Molded and tested in accordance with ASTM D4976.

Note: These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.





Luban DMDA-8007 High Density Polyethylene



Storage and Handling

Luban DMDA-8007 should be stored in well ventilate area during handling or processing of to prevent accumulation of dust and fumes. Avoid contact with strong oxidizers, excessive heat, sparks or open flame as this could well speed up alteration and consequently loss of quality of the material in which could lead to unforeseen dangers. The bags must be protected from direct sunlight and should be stored in shaded and completely dry area for good processing.

Safety

Luban DMDA-8007 is not classified as dangerous preparation. For further information about safety in handling and processing please refer to the Safety Data Sheet.

Food Contact

Luban DMDA-8007 meets the requirements of the U.S. Food and Drug Administration (FDA) as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Product Stewardship Declaration".

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Updated: Oct. 2019

Disclaimer:

Values given here are typical and should not be interpreted as specification. Before using ORPIC product, customers and other users should make their own independent determination that the product is suitable for the intended use. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under ORPIC or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of ORPIC except in a writing signed by an authorized ORPIC employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at ORPIC's option, and in no event shall ORPIC be liable for special, consequential, incidental, punitive or exemplary damages.

